




- EMI, RFI, ESD Protection
- Grounding Straps
- Engine Dress-Up
- Complies With
CID A-A-59569
- Extreme Blowout
Protection
- Expands For Easy
Installation
- Cut And Abrasion
Resistant



Cut Cleanly
Shears

Material

Silver Plated

Grade

MBS

Wire Thickness

.005" - .010"

Put-Ups

Nominal Size	Part #	Wall Thickness	Wire Thickness	Bulk Spool	Shop Spool	Available Colors	Lbs/100'
1/16"	MBS0.06SV	0.013"	0.005"	250'	100'	Silver (SV)	0.40
7/64"	MBS0.11SV	0.013"	0.005"	250'	100'	Silver (SV)	0.80
1/8"	MBS0.13SV	0.013"	0.005"	250'	100'	Silver (SV)	1.00
5/32"	MBS0.16SV	0.013"	0.005"	250'	100'	Silver (SV)	2.10
11/64"	MBS0.17SV	0.013"	0.005"	250'	100'	Silver (SV)	1.35
13/64"	MBS0.20SV	0.020"	0.008"	250'	100'	Silver (SV)	2.50
1/4"	MBS0.25SV	0.013"	0.005"	250'	100'	Silver (SV)	2.20
3/8"	MBS0.38SV	0.013"	0.005"	250'	100'	Silver (SV)	3.30
1/2"	MBS0.50SV	0.013"	0.005"	100'	50'	Silver (SV)	3.50
5/8"	MBS0.63SV	0.016"	0.006"	100'	50'	Silver (SV)	3.60
25/32"	MBS0.78SV	0.013"	0.005"	100'	50'	Silver (SV)	7.35
7/8"	MBS0.88SV	0.025"	0.010"	100'	50'	Silver (SV)	10.30
1"	MBS1.00SV	0.025"	0.010"	100'	50'	Silver (SV)	13.15
1 1/8"	MBS1.13SV	0.025"	0.010"	100'	50'	Silver (SV)	13.80
1 1/4"	MBS1.25SV	0.025"	0.010"	100'	50'	Silver (SV)	16.50
1 3/8"	MBS1.38SV	0.025"	0.010"	100'	50'	Silver (SV)	16.90
1 1/2"	MBS1.50SV	0.025"	0.010"	100'	50'	Silver (SV)	18.40
2"	MBS2.00SV	0.025"	0.010"	100'	50'	Silver (SV)	22.70
2 1/4"	MBS2.25SV	0.025"	0.010"	100'	50'	Silver (SV)	23.60


**Flexo Silver Plated For Intense Shielding
And Grounding Environments**

Colors Available:
Silver (SV)

FLEXO SILVER PLATED COPPER BRAID (MBS) is made to conform to AA59569 and ASTM-B298. MBS products are produced with a minimum plating thickness of 40 micro-inches.

Federal Specification QQ-B-575C, dated September 22, 1993 was replaced on November 20, 2000 and replaced by Commercial Item Description (CID) A-A-59569. This CID covers tin- or silver-plated copper wire braids supplied in tubular or flat form intended for use as shielding over electrical conductors, controller contacts and grounding bonds.


USE: Silver plating, in lieu of tin plating, is necessary when the shielding is to be subjected to temperatures exceeding 150°C or if special corrosion resistance is required.



www.techflex.com

800.323.5140 • 973.300.9242 • fax: 973.300.9409
104 Demarest Road • Sparta, NJ 07871






FLAMMABILITY

Rating _____ Non Flammable

Melt Point
ASTM D-2117
Copper 1,981°F (1,083°C)
Silver 1,762°F (961°C)



CHEMICAL RESISTANCE

1=No Effect 4=More Affected
2=Little Effect 5=Severely Affected
3=Affected

Aromatic Solvents _____ 1
Aliphatic Solvents _____ 1
Chlorinated Solvents _____ 1
Weak Bases _____ 1
Salts _____ 1
Strong Bases _____ 2
Salt Water 0-S-1926 _____ 1
Hydraulic Fluid MIL-H-5606 _____ 1
Lube Oil MIL-L-7808 _____ 1
De-Icing Fluid MIL-A-8243 _____ 1
Strong Acids _____ 5
Strong Oxidants _____ 5
Esters/Ketones _____ 1
UV Light _____ 2
Petroleum _____ 2
Fungus ASTM G-21 _____ 2
Halogen Free _____ Yes
RoHS _____ Yes

PHYSICAL PROPERTIES

Monofilament Diameter _____ .005-.010
ASTM D-204
Flammability Rating _____ Non Flammable
Recommended Cutting _____ Shears
Colors _____ 1
Wall Thickness _____ .013-.025
Specific Gravity ASTM D-792 _____ 8.9
Moisture Absorption _____ NA
% ASTM D-570

Nominal Size	Part #	AWG of Ends	Carriers	Wires Per Carrier	Current Capacity Amps
1/16"	MBS0.06SV	36	24	2	11
7/64"	MBS0.11SV	36	24	4	19
1/8"	MBS0.13SV	36	24	5	25
5/32"	MBS0.16SV	36	24	10	40
11/64"	MBS0.17SV	36	24	7	32
13/64"	MBS0.20SV	32	24	5	46
1/4"	MBS0.25SV	36	24	16	53
3/8"	MBS0.38SV	36	48	5	53
1/2"	MBS0.50SV	36	48	11	62
*5/8"	MBS0.63SV	34	48	8	64
25/32"	MBS0.78SV	36	48	18	88
7/8"	MBS0.88SV	30	48	7	100
1"	MBS1.00SV	30	48	8	120
1 1/8"	MBS1.13SV	30	48	9	130
*1 1/4"	MBS1.25SV	30	48	10	145
1 3/8"	MBS1.38SV	30	48	11	150
1 1/2"	MBS1.50SV	30	48	12	165
2"	MBS2.00SV	30	48	14	180
*2 1/4"	MBS2.25SV	30	48	16	190

*Not on Spec - CID A-A-59569 (formerly Mil Spec QQB-575)